

# NewsPress

by Stora Enso



NewsPress is a standard newsprint grade. It is available with several combinations of recycled and primary fibre.

- Outstanding runnability
- Excellent in four colour printing
- Produced according to Ifra standard

## PRODUCER

Langerbrugge Mill  
Hylte Mill  
Sachsen Mill

## TYPICAL END USES

Newspapers  
Supplements  
Free sheets

## COLOUR PROFILE

ISOnewspaper26v4

## L\* a\* b\* target values

	L*	a*	b*	Flourescence (ISO 12647-2)
Langerbrugge ISO 5631-3 (D50/2°)	83	0.4	4.5	Faint
Hylte ISO 5631-3 (D50/2°)	82.9	-0.7	4.8	Faint
Sachsen ISO 5631-3 (D50/2°)	82.5	-0.3	4.5	Faint

## CHARACTERISATION DATA

WAN-IFRA

## PRINTING METHODS

CSWO  
(HSWO)

## TECHNICAL SPECIFICATIONS LANGERBRUGGE - 100% recycled fibre (target values)

Substance	ISO 536	g/m <sup>2</sup>	40	42	42.5	45	48.8
Brightness	ISO 2470, C/2°	%	58.5	58.5	58.5	58.5	58.5
Opacity	ISO 2471 (D65/10°)	%	92	93	93	94	95
Caliper	ISO 534	µm	59	62	62	64	68
Smoothness	PPS 1MPa, ISO 8971-2	µm	4.3	4.3	4.3	4.3	4.3

## TECHNICAL SPECIFICATIONS HYLTE - 50% recycled fibre (target values)

Substance	ISO 536	g/m <sup>2</sup>	40	42.5	45	48.8
Brightness	ISO 2470, C/2°	%	57	57	57	57
Opacity	ISO 2471 (C/2°)	%	91.5	92.5	94	94.5
Caliper	ISO 534	µm	62	67	70	73
Smoothness	PPS 1MPa, ISO 8971-2	µm	4.2	4.2	4.2	4.2

## TECHNICAL SPECIFICATIONS SACHSEN - 100% recycled fibre (target values)

Substance	ISO 536	g/m <sup>2</sup>	40	42.5	45
Brightness	ISO 2470, C/2°	%	58.5	58.5	58.5
Opacity	ISO 2471 (D65/10°)	%	91	92	93
Caliper	ISO 534	µm	58	61	64
Roughness	Bendtsen ISO 8791-4	µm	140	140	140

## REEL SPECIFICATIONS

Core for all mills: 76 mm  
Max trimmed width:  
Hylte: 840 cm  
Langerbrugge: 1036/1037 cm  
Sachsen: 920 cm

## CERTIFICATES

ISO 9001  
ISO 14001  
ISO 50001  
OHSAS 18001  
FSC® CoC, license code FSC® C015932  
PEFC™ CoC, licence code PEFC/02-31-86

## ENVIRONMENT

Renewable fibre  
Recyclable paper  
Recyclable packaging materials

## STORAGE AND HANDLING

- Store the paper in a humidity and temperature controlled area at 50% relative humidity and room temperature between 19°C and 23°C.
- If the paper is stored in non-air conditioned warehouse, it is absolutely necessary to allow a stabilisation period in the print room.
- Open the protective wrapping at the moment of use.

PRINT MEDIA: Newsprint

Updated: 06 June 2017