



Data table - Technical specifications, typical values

Grammage , g/m ² , ISO 536	120	127	140	150	160	175	190*
Thickness μm, ISO 534	170	180	200	220	230	250	280
Moisture , % (in delivered reel) ISO 287	10	10	10	10	10	10	10
CMT 30 , N, ISO 7263	290	320	380	420	460	490	**
CCT 30 , kN/m, SCAN-P42	2,7	2,9	3,3	3,6	3,9	4,4	4,7
Air resistance , s, ISO 5636-5	100	100	100	100	100	100	100

Test climate 23°C/50% RH (according to ISO 187)

*Target values of this grammage. **CMT30 test is not valid for grammage greater than 190 g/m².

Reel diameters: 125, 145 cm. Reel core size: 10 cm.

Ideal storage conditions: 23°C/50% RH

Paper should be stored in a dry, covered and ventilated warehouse. It is recommended that prior to use in production, paper should be stored some time in conditions similar to the conditions in the production hall. The required storage period depends mainly on the volume of paper reel, as well as the temperature difference between the warehouse and production hall.

Certificates

- ISO 9001
- ISO 14001
- ISO 22000
- ISO 50001
- OHSAS 180001
- FSC Chain of Custody
- PEFC Chain of Custody

Producing mill: Heinola, Finland

Updated 30 June 2017

